



Chemical resistance silicones

Chemical resistance of silicone rubber

In answer to questions regarding the effects of solvents and industrial chemicals on silicone rubber, the following data have been compiled.

Silicone are in general, chemically inert and are attacked by only a very few common materials. Among them are concentrated sulphuric acid, hydrofluoric acid and under long term exposure, high pressure steam.

Like any elastomer, silicone has a tendency to physically absorb those materials with a solubility parameter near its own. This absorption may cause the rubber to swell and to soften slightly. In few applications, this volume increase is advantageous.

For example, a silicone rubber gasket exposed to certain solvents will swell to form a tighter seal. The change undergone by silicone rubber in contact with an absorbed solvent is primarily physical. After the solvent has completely evaporated, the silicone rubber will return to its original physical properties.

Limitations & liability

The main experience of Den Braven Sealants is in sealants for building and glazing joints. Knowledge of and experience in chemical resistant sealants and joints is limited.

Chemical resistance strongly depends on concentration, temperature and exposure time.

That is why Den Braven Sealants does not give any guaranty on chemical resistance. However we can, without any warranty, provide the knowledge and experience of our raw material supplier in the format of this chemical resistance list.

It is the responsibility of the user to verify by his own tests if the product is suitable for the application.

Warranty

Den Braven Sealants warrants that the product complies, within its shelf life, to its specification. The liability shall in no case exceed the amount fixed in our Condition of Sale.

In no event Den Braven Sealants is liable for any kind of incidental or consequential damages. The following table shows silicone resistance to various common materials.

It indicates the volume change which may be expected from silicone rubber submerged in a chemical or solvent for one week at room temperature. The following definitions for solvent resistance were arbitrarily assigned:

- 1 = excellent, less than 10% volume change
- 2 = good, 10-25% volume change
- 3 = fair, 25-75% volume change
- 4 = poor, greater than 75% volume change
- 5 = disintegrates

Acids

Citric	1
Hydrochloric, 3% and Conc.	1
Hydrofluoric	5
Phosphoric, dilute	1
Sulphuric, 10%	1
Sulphuric, Conc.	5
Nitric, 7% and Conc.	1-2
Acetic, 5% and Conc.	1

Basis

Ammonium Hydroxide, 10%	1
Ammonium Hydroxide, Conc.	1
Potassium Hydroxide	1
Sodium Hydroxide, 5% and 50%	1

Inorganic Chemicals

Anhydrous Ammonia	1
Sodium Chloride, 10%	1
Hydrogen Peroxide, 3%	1
Sodium Carbonate, 20%	1
Water / Water 70 Hrs @ 212°F	1

Organic Chemicals

Detergents	1
Freon 12	2
Freon 114	3
Methyl Chloride	3
Tricresyl Phosphate	1

Hydraulic Fluids

Hollingshead, H-2	1
Hollingshead, H-2, 70 Hrs @ 212°F	2
Skydrol 500	3
Skydrol 8000 also after 70 Hrs @ 212°F	1
Silicate Base	3

Oils

ASTM#10.1 aliphatic, 70 Hrs @ 300°F	1
ASTM#30.1 aromatic, 70 Hrs @ 300°F	3
Castor 0.1	1
Diester oils	2
Linseed oil / Mineral oil	1
Silicone oil also after 70 Hrs @ 300°F	3

Solvents

Acetone	3
Butyl Alcohol	2
Carbon Tetrachloride	4
Diaceton Alcohol / Ethyl Alcohol	1
Gasoline	4
Jet Fuel, JP4	3
Mineral Spirits & Toluene	4

The information in this document and also in all our print and digital publications is based on our present knowledge and experience. Den Braven cannot be held responsible for any mistakes, inaccuracies or editorial faults that result from technological changes or research between the date of issue of this document and the date the product is acquired. Den Braven reserves the right to make changes to formulations. Before applying the product the user should acquaint themselves with the information presented in this document and/or in our other product related documents. Before applying the product the user should carry out any necessary tests to ensure the product is suitable for the application. The application method, conditions during storage and transport fall beyond our control and therefore responsibility. Liability under this product sheet cannot be accepted. Deliveries only in accordance with our conditions of delivery and payment terms. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive.